

TileFlex 2000®

The Next Generation In Roof Coating Technology

TileFlex 2000®¹ is no ordinary paint. This revolutionary coating combines advanced technology developed exclusively by Nutech Paint over more than 30 years with the special properties of surface cleaning Nano Technology to deliver superior performance.

Nutech Paint have spent years developing TileFlex 2000® roof coating, which will stay cleaner and retain gloss longer than any conventional acrylic roof coating.

Independent CSIRO² testing has conclusively shown that the surface friction of TileFlex 2000® is substantially reduced by the unique properties of surface cleaning Nano Technology. Special polymers used in the manufacture of TileFlex 2000® and a low level of surface friction enables the coating to repel moisture, dirt and contamination. This will greatly improve the appearance and function of your roof.

Further testing has shown that TileFlex 2000® has superior gloss, early water resistance and film drying speed compared to other acrylic coatings enhancing appearance and application properties.

TileFlex 2000® provides significantly more gloss on application and will maintain an attractive new looking roof appearance better than any other acrylic roof coating.

To reduce the damaging effects of the harsh Australian environment, Nutech has used the latest technology to impregnate TileFlex 2000® with surface cleaning Nano Technology. This innovation guarantees that TileFlex 2000® sets new standards in roof coating performance, maximizing the durability and total waterproof protection.

Technical Information

Classification	Non flammable
Tinting	38 standard & custom colours available
Thinning	Not required (water clean up)
Shelf Life	12 months
Minimum Film Forming Temperature	10°C
Drying Time @ 25 Degrees Celsius	Touch dry: 20 minutes
Recoat Time	1 hour – new pointing must be cured
Application Temperature	14 – 30 Degrees Celsius
Total Solids	>40%
Film Thickness (two coats)	200 microns (dry film)
Gloss Level	High gloss
Application	Brush, roller, airless spray gun (spray tip 523)
Containers	4lt, 10lt, 20lt, 200lt, 1000lt
Recommended Application Rate	2 coats @ 4 square metres per litre per coat

¹ TileFlex 2000 is a Registered Trademark of Nutech Paint Pty Ltd

² CSIRO Report DBCE Doc 96/168(M) available for inspection at Nutech Paint Pty Ltd

TileFlex 2000®

Protect Your Roof with TileFlex 2000®

There are two important reasons why you should restore your roof. Firstly, the appearance of your home is greatly improved with a clean glossy coloured roof. Secondly, and more importantly, a durable coating protects your roof from the effects of ageing.

All exterior surfaces and coatings undergo an ageing process caused by moisture, UV light radiation, temperature extremes, dirt, pollution, moss, lichen and bacteria. This ageing can result in gloss reduction, chalking, discolouration, blistering, flaking, loss of adhesion, and unsightly moss and lichen build up resulting in general coating failure.

The key to the success of TileFlex 2000® is its amazing ability to resist the causes of ageing better than any other acrylic roof coating. TileFlex 2000® uses a unique system of surface cleaning Nano Technology to repel dirt pick up and contamination.

TileFlex 2000® contains highly effective polymer preservatives which provide long lasting broad spectrum, algacide and fungicide protection to prevent polymer discolouration and deterioration and moss and lichen growth. Unlike many other roof coatings, TileFlex 2000® is also user friendly because it does not contain environmentally harmful formaldehyde preservatives. TileFlex 2000® is suitable for the collection of drinking water.

TileFlex 2000® contains UV resistant non-fading pigments and tough flexible 100% acrylic polymers which will transform any roof into an attractive and functional surface. TileFlex 2000® is guaranteed not to peel, fade or crack subject to correct surface preparation and application.

With TileFlex 2000® you can be confident that you will obtain “a perfect finish” every time.

Application Warnings

Do not apply TileFlex 2000® in very low temperatures to avoid coating adhesion problems.

Do not overcoat Nu-Prime, Master Sealer or Nu-Bond until the undercoat is completely dry.

Coating in very hot conditions may reduce gloss appearance.

Refer to the Material Safety Data Sheet for additional safety and user information.

Important Note

The information given on this data sheet is based on many years experience and is correct to the best of our knowledge. However since the use of our product, surface conditions, weather and a number of other factors are completely beyond our control, we can only be responsible for the quality of our product at the time of dispatch. For more information please contact our Company. As this information is of a general nature, we cannot assume any responsibility in individual cases.